


Polypropylene ISO 1346 3 strand

CONSTRUCTION

Three-strand ropes of the POLYPROPYLENE range are well established in marine and off-shore applications, it is the most traditional design. They are produced on laying machines, giving a round rope with excellent strength characteristics and bending fatigue.



MATERIAL PROPERTIES

For rope polypropylene is most often produced as split film. This means a firm is extruded and is split using knives before drawing. The strength is obtained in this drawing process. Other fibres are mostly produced as multi-filament. Polypropylene is chemically inert, has a low density (it floats), but has a somewhat lower melting point and lower strength.

FEATURES


- Material: Standard polypropylene
- Construction: 3 strand laid
- Treatment: None
- Colour of Rope: Diverse

- Approx. Spec. Density: 0,91 floating
- Melting Point: 165° C
- Abrasion Resistance: Low
- U.V.resistance: Low
- Temperature resistance: 70°C max continuous
- Chemical resistance: Good, solvents and strong oxidisers may have a mild effect

- Dry & wet conditions: Wet strength equals dry strength

- Range of use: Fishing, inland shipping, merchant, navy, industry, mooring

Dia mm	Circ. "	Min Break Load		Weight	
		tf	kN	kg/100m	kg/coil
6	3/4	0,60	5,90	1,70	3,74
8	1	1,06	10,4	3,00	6,60
10	1 1/4	1,56	15,3	4,50	9,90
12	1 1/2	2,21	21,7	6,50	14,3
14	1 3/4	3,05	29,9	9,00	19,8
16	2	3,78	37,0	11,5	25,3
18	2 1/4	4,80	47,0	14,8	32,6
20	2 1/2	5,81	56,9	18,0	39,6
22	2 3/4	6,96	68,2	22,0	48,4
24	3	8,13	79,7	26,0	57,2
26	3 1/4	9,41	92,2	30,5	67,1
28	3 1/2	10,7	105	36,0	79,2
30	3 3/4	12,2	120	41,3	90,9
32	4	13,5	132	46,0	101
36	4 1/2	16,9	166	59,5	131



Coil length: 220m
 Spliced strength: ± 10% lower
 Weight and length tolerance: ± 5%
 Diameter: ± 2%

MBL = Minimum Breaking Load conform ISO 2307
 Other sizes available upon request

The information disclosed herein was originated by and is the property of BEXCO nv and its subsidiaries. BEXCO nv and its subsidiaries reserves all intellectual and industrial property rights such as any and all patent, trademark, design, manufacturing, reproduction use and sales rights thereto and to any article disclosed therein, except to the extent rights expressly granted to others.